



Timeless natural hues

N° 1019168

## FRENCH OAK ZENITUDE CAFÉ CRÈME, DIVA 139 CLICK / 12 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade: Zenitude** - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all of the peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

**Finish: Café crème** - brushed, coffe latte tone matt lacquered / Ecostrong lacquer - Gloss: 4/6

### Design

Engineered wide single plank made under the patent EN 13489  
Click system under Unilin patent n°EP1640530

### Description

**Width:** 139 mm  
**Length:** 495 to 1992 mm  
**Thickness:** 12 mm  
**Top layer:** 2.5 mm  
**Core:** HDF\*  
**Counterbalance:** unrolled wood  
**Profile:** 4 bevels

\*High Density Fiber Board

### Packing

**Sqm/-pack:** 1.38  
**Pack/pallet:** 65  
**Sqm/pallet:** 89.70  
**Weight/sqm:** 9.9 kg  
**Weight/pallet:** 888.0 kg



### Installation method



Glue-free floating under  
the patent DTU 51.11




Glue down installation  
under the patent DTU 51.2




Floating installation using  
plastic DPM and Isol 20 or fully  
glue down using Presto PM



Fully glue down using  
Presto PM



\* Emissions of volatile substances which could be toxic if inhaled. These are rated on a scale from A+ (very low) to C (high).



# DECLARATION OF PERFORMANCE

## N° 1019168



**Unique identification code of the product-type:** Diva 139 Click, 12 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

### Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction of fire	Dfl-s1	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> ) - Average thickness (mm) - Intended use, fitting mode	500 12 Floating fit		
Formaldéhyde emission	E1		EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1 µg/m <sup>3</sup>	ISO 16000	
Breaking strength	N/A	-	
Slipperiness	N/A	-	
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapter 4.7	
Thermal resistance (m <sup>2</sup> .K/W)	0,08		
Biological sustainability	Class 1	EN 335	
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-	
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-	

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

**Carole FRANÇOIS**

