



Daylight whites



N° 1006929

## FRENCH OAK TRADITION SAPHIR, ORFÉO 139 CLICK / 14 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade: Tradition** - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, filled cracks, sapwood.

**Finish: Saphir** - brushed, white matt lacquered / Ecostrong lacquer - Gloss: 4/6

While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin 2-5% more than the actual you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

### Design

Engineered two-strip made under the patent EN 13489  
Click system under Unilin patent n°EP1640530

### Description

**Width:** 139 mm  
**Length:** 1500 mm  
**Thickness:** 14 mm  
**Top layer:** 3.4 mm  
**Core:** HDF\*  
**Counterbalance:** unrolled wood  
**Profile:** square edges

\*High Density Fiber Board



### Packing

**Sqm/pack:** 1.46  
**Pack/pallet:** 50  
**Sqm/pallet:** 73.00  
**Weight/sqm:** 11.8 kg  
**Weight/pallet:** 861.4 kg

### Installation method




Glue-free floating under  
the patent DTU 51.11




Glue down installation  
under the patent DTU 51.2



Floating installation using  
plastic DPM and Isol 20 or fully  
glue down using Presto PM



\* Emissions of volatile substances which could be toxic if inhaled. These are rated on a scale from A+ (very low) to C (high).



# DECLARATION OF PERFORMANCE

N° 1006929



**Unique identification code of the product-type:** Orféo 139 Click, 14 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

## Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction of fire	Dfl-s1	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> ) - Average thickness (mm) - Intended use, fitting mode	500 14 Floating fit		
Formaldéhyde emission	E1		EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1 µg/m <sup>3</sup>	ISO 16000	
Breaking strength	N/A	-	
Slipperiness	N/A	-	
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7	
Thermal resistance (m <sup>2</sup> .K/W)	0.09		
Biological sustainability	Class 1	EN 335	
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-	
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-	

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

**Carole FRANÇOIS**

