



PANAGET

manufacture française de parquet
DEPUIS 1929



N° 1000034

Timeless natural hues

FRENCH OAK AUTHENTIC TOPAZE, SONATE 140 TONGUE & GROOVE / 14 MM

Characteristics

Species: French oak **Origin:** France

Grade: Authentic - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, cracks. The size of the knots is proportional to the width of the plank.

Finish: Topaze - brushed, matt lacquered / Ecostrong lacquer - Gloss: 4/6

Design

Solid single plank made under the patent EN 13226
Tongue & Groove



Description

Width: 140 mm
Length: 400 to 1300 mm
Thickness: 14 mm
Top layer: 7.0 mm
Core:
Counterbalance: no
Profile: 4 bevels

Packing

Sqm/pack: 1.64
Pack/pallet: 40
Sqm/pallet: 65.60
Weight/sqm: 10.7 kg
Weight/pallet: 701.9 kg

Installation method




Glue down installation
under the patent DTU
51.2



Floating installation gluing T&G
using plastic DPM and Isol 20 or
fully glue down using Presto PM



* Emissions of volatile substances which could be toxic if inhaled. These are rated on a scale from A+ (very low) to C (high).



PANAGET - 3 rue d'Orgères - 35230 Bourgarré - FRANCE
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // www.panaget.com



DECLARATION OF PERFORMANCE

N° 1000034

Unique identification code of the product-type: Sonate 140 Tongue & Groove, 14 mm, French oak

Intended use/es: Solid single plank made under the patent EN 13226

Glue down installation under the patent DTU 51.2

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification:		
- Average minimum density (Kg/m ³)	650	
- Average thickness (mm)	14	
- Intended use, fitting mode	Glued to the subfloor	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances:		ISO 16000
- VOC* emissions (Decree No 2011-321)	Class A+	
- CMR 1&2** emissions (Decree n° DEVP0910046A)	< 1 µg/m ³	
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.17	EN 14342 / Chapter 4.7
Thermal resistance (m ² .K/W)	0.08	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	8.5 kg.CO ₂ /m ²	-
FDES 2022 - Life Cycle impact assessment	1.4 kg éq. CO ₂ /m ²	-

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

Carole FRANÇOIS

