



Timeless natural hues

N° 1019822

FRENCH OAK AUTHENTIC CAFÉ CRÈME, CHEVRON 139 TONGUE & GROOVE / 14 MM

Characteristics

Species: French oak **Origin:** France

Grade: Authentic - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, cracks. The size of the knots is proportional to the width of the plank.

Finish: Café crème - brushed, coffee latte tone matt lacquered / Ecostrong lacquer - Gloss: 4/6

Design

Engineered single plank chevron made under the patent EN 13489
Tongue & Groove

Description

Width: 139 mm
Length: 650 mm
Thickness: 14 mm
Top layer: 3.4 mm
Core: plywood
Counterbalance: unrolled wood
Profile: 4 bevels

Packing

Sqm/pack: 1.45
Pack/pallet: 32
Sqm/pallet: 46,40
Weight/sqm: 7.4 kg
Weight/pallet: 343.4 kg



Installation method





Floating glued
installation under the
patent DTU 51.11



Glue down installation
under the patent DTU 51.2



Floating installation gluing T&G
using plastic DPM and Isol 20 or
fully glue down using Presto PM



DECLARATION OF PERFORMANCE

N° 1019822



Unique identification code of the product-type: Chevron 139 Tongue & Groove, 14 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m ³)	500	
- Average thickness (mm)	14	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321)	Class A+	ISO 16000
- CMR 1&2** emissions (Decree n° DEVP0910046A)	< 1 µg/m ³	
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.13	EN 14342 / Chapter 4.7
Thermal resistance (m ² .K/W)	0.11	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO ₂ /m ²	-

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

Carole FRANÇOIS

