



Daylight whites

N° 1007639

FRENCH OAK ZENITUDE TUFEAU, DIVA 139 CLICK / 12 MM

Characteristics

Species: French oak **Origin:** France

Grade: Zenitude - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all of the peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

Finish: Tufeau - brushed, chalk-tone matt oiled / Oil - Gloss: 4/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide. While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin of 2-5% more than the actual you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

Design

Engineered wide single plank made under the patent EN 13489
 Click system under Unilin patent n°EP1640530

Description

Width: 139 mm
Length: 495 to 1992 mm
Thickness: 12 mm
Top layer: 2.5 mm
Core: HDF*
Counterbalance: unrolled wood
Profile: 4 bevels

*High Density Fiber Board

Packing

Sqm/pack: 1.38
Pack/pallet: 65
Sqm/pallet: 89.70
Weight/sqm: 9.9 kg
Weight/pallet: 888.0 kg



Installation method



Glue-free floating under
 the patent DTU 51.11




Glue down installation
 under the patent DTU 51.2



Floating installation using
 plastic DPM and Isol 20 or fully
 glue down using Presto PM



Fully glue down using
 Presto PM



DECLARATION OF PERFORMANCE

N° 1007639



Unique identification code of the product-type: Diva 139 Click, 12 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

| Essential features | Performances | Appropriate Technical Documentation and/or Specific Technical Documentation | |
|---|--|---|----------|
| Reaction of fire | Dfl-s1 | EN 14342 : 2013 | |
| Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode | 500 12 Floating fit | | |
| Formaldéhyde emission | E1 | | EN 717-1 |
| Content of pentachlorophenol | PCP ≤ 5 ppm | | - |
| Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A) | Class A+ < 1 µg/m ³ | ISO 16000 | |
| Breaking strength | N/A | - | |
| Slipperiness | N/A | - | |
| Thermal conductivity (W/m.K) | 0,15 | EN 14342 / Chapter 4.7 | |
| Thermal resistance (m ² .K/W) | 0,08 | | |
| Biological sustainability | Class 1 | EN 335 | |
| RE2020 - Building Carbon Index | 3 kg.CO ₂ /m ² | - | |
| FDES 2022 - Life Cycle impact assessment | 8.6 kg éq. CO ₂ /m ² | - | |

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

Carole FRANÇOIS

