



Daylight whites

PANAGET

manufacture française de parquet
DEPUIS 1929



N° 1007320

FRENCH OAK ZENITUDE LINEN, DIVA 184 CLICK / 12 MM

Characteristics

Species: French oak **Origin:** France

Grade: Zenitude - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all of the peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

Finish: Linen - brushed, light white matt lacquered/ Ecostrong lacquer - Gloss: 4/6

While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin 2-5% more than the actual you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

Design

Engineered extra-wide single plank made under the patent EN 13489
Click system under Unilin patent n°EP1640530

Description

Width: 184 mm
Length: 495 to 1992 mm
Thickness: 12 mm
Top layer: 2.5 mm
Core: HDF*
Counterbalance: unrolled wood
Profile: 4 bevels

*High Density Fiber Board

Packing

Sqm/pack: 2.20
Pack/pallet: 40
Sqm/pallet: 88.00
Weight/sqm: 9.9 kg
Weight/pallet: 871.2 kg



Installation method



Glue-free floating under
the patent DTU 51.11





Glue down installation
under the patent DTU 51.2



Floating installation using
plastic DPM and Isol 20 or fully
glue down using Presto PM



Fully glue down using
Presto PM



DECLARATION OF PERFORMANCE

N° 1007320



Unique identification code of the product-type: Diva 184 Click, 12 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction of fire	Dfl-s1	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode	500 12 Floating fit		
Formaldéhyde emission	E1		EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1 µg/m ³	ISO 16000	
Breaking strength	N/A	-	
Slipperiness	N/A	-	
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapter 4.7	
Thermal resistance (m ² .K/W)	0,08		
Biological sustainability	Class 1	EN 335	
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-	
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO ₂ /m ²	-	

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

Carole FRANÇOIS

