



Elegant browns

N° 1006550

## FRENCH OAK ZENITUDE-ORIGINE CUIR, DIVA 184 TONGUE & GROOVE / 14 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade: Zenitude-Origine** - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all of the peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks. Aged bevels. UV-cured

**Finish: Cuir** - brushed, old leather-tone matt oiled / Oil - Gloss: 4/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide.

### Design

Engineered extra-wide single plank made under the patent EN 13489 Tongue & Groove

### Description

- Width:** 184 mm
- Length:** 500 to 2000 mm
- Thickness:** 14 mm
- Top layer:** 3.4 mm
- Core:** plywood
- Counterbalance:** unrolled wood
- Profile:** 2 aged bevels



### Packing

- Sqm/pack:** 1.84
- Pack/pallet:** 44
- Sqm/pallet:** 80.96
- Weight/sqm:** 7.4 kg
- Weight/pallet:** 599.1 kg

### Installation method




Floating glued installation under the patent DTU 51.11




Glue down installation under the patent DTU 51.2



Floating installation gluing T&G using plastic DPM and Isol 20 or fully glue down using Presto PM



\* Emissions of volatile substances which could be toxic if inhaled. These are rated on a scale from A+ (very low) to C (high).



# DECLARATION OF PERFORMANCE

N° 1006550



**Unique identification code of the product-type:** Diva 184 Tongue & Groove, 14 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

## Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> )	500	
- Average thickness (mm)	14	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1 µg/m <sup>3</sup>	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.13	EN 14342 / Chapter 4.7
Thermal resistance (m <sup>2</sup> .K/W)	0.11	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

**Carole FRANÇOIS**

