



Timeless Natural Hues

N° 1021063

FRENCH OAK ZENITUDE BOIS FLOTTÉ HIGH TRAFFIC, HERRINGBONE 139 TONGUE & GROOVE / 14 MM

Characteristics

Species: French oak **Origin:** France

Grade: Zenitude - light and dark wood, black knots, filled knots, opened knots, discolouration, cracks, splits, sapwood. Grade with all peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

Finish: Bois flotté High Traffic - brushed, matt lacquered with unfinished aspect / GT high traffic lacquer - Shine (gloss): 4/6

Design

Engineered single plank, herringbone made under the patent EN 13489 Tongue & Groove

Description

Width: 139 mm
Length: 800 mm
Thickness: 14 mm
Top layer: 3.4 mm
Core: plywood
Counterbalance: unrolled wood
Profile: 4 bevels



Packing

Sqm/pack: 2.22
Pack/pallet: 32
Sqm/pallet: 71.04
Weight/sqm: 7.4 kg
Weight/pallet: 1 167.2 kg

Installation method





Floating glued installation under the patent DTU 51.11



Glue down installation under the patent DTU 51.2



Floating installation gluing T&G using plastic DPM and Isol 20 or fully glue down using Presto PM



DECLARATION OF PERFORMANCE

N° 1021063



Unique identification code of the product-type: Herringbone 139 Tongue & Groove, 14 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m ³)	500	
- Average thickness(mm)	14	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1µg/m ³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.13	EN 14342 / Chapter 4.7
Thermal resistance (m ² .K/W)	0.11	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-
FDES 2022 - Life Cycle impact assessment	8,6 kg éq. CO ₂ /m ²	-

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023
Carole FRANÇOIS

