



Daylight whites

# PANAGET

manufacture française de parquet  
DEPUIS 1929



N° 1005924

## FRENCH OAK CLASSIC/AUTHENTIC LINEN, HERRINGBONE 90 TONGUE & GROOVE / 12 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade: Classic/Authentic** - light and dark wood, black knots, filled knots, partially opened knots, medular rays, traces of discolouration, black marks, cracks. The size of the knots is proportional to the width of the plank.

**Finish: Linen** - brushed, light white matt lacquered/ Ecostrong lacquer - Gloss: 4/6

While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin of 2-5% more than the actual you're covering. This means you won't run out of planks and you will be sure to enjoy a beautiful finished product.

### Design

Engineered single plank, herringbone patterns made under the patent EN 13489  
Tongue & Groove

### Description

**Width:** 90 mm  
**Length:** 590 mm  
**Thickness:** 12 mm  
**Top layer:** 2.5 mm  
**Core:** HDF\*  
**Counterbalance:** unrolled wood  
**Profile:** 4 bevels

\*High Density Fiber Board

### Packing

**Sqm/pack:** 1.91  
**Pack/pallet:** 32  
**Sqm/pallet:** 61.12  
**Weight/sqm:** 9.9 kg  
**Weight/pallet:** 605.1 kg



### Installation method



Floating glued  
installation under the  
patent DTU 51.11





Glue down installation  
under the patent DTU 51.2



Floating installation gluing T&G  
using plastic DPM and Isol 20 or  
fully glue down using Presto PM



Fully glue down using  
Presto PM



# DECLARATION OF PERFORMANCE

N° 1005924



**Unique identification code of the product-type:** Herringbone 90 Tongue & Groove, 12 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

## Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> )	500	
- Average thickness (mm)	12	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1 µg/m <sup>3</sup>	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapter 4.7
Thermal resistance (m <sup>2</sup> .K/W)	0,08	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

**Carole FRANÇOIS**

