



Timeless natural hues

# PANAGET

manufacture française de parquet  
DEPUIS 1929



N° 1000028

## FRENCH OAK AUTHENTIC TOPAZE, SONATE 90 TONGUE & GROOVE / 14 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade: Authentic** - light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, cracks. The size of the knots is proportional to the width of the plank.

**Finish: Topaze** - brushed, matt lacquered / Ecostrong lacquer - Gloss: 4/6

### Design

Solid single plank made under the patent EN 13226  
Tongue & Groove



### Description

**Width:** 90 mm  
**Length:** 400 to 1300 mm  
**Thickness:** 14 mm  
**Top layer:** 7.0 mm  
**Core:**  
**Counterbalance:** non  
**Profile:** 4 bevels

### Packing

**Sqm/pack:** 1.64  
**Pack/pallet:** 32  
**Sqm/pallet:** 52.48  
**Weight/sqm:** 10.7 kg  
**Weight/pallet:** 561.5 kg


### Installation method




Glue down installation  
under the patent DTU  
51.2



Floating installation gluing T&G  
using plastic DPM and Isol 20 or  
fully glue down using Presto PM



\* Emissions of volatile substances which could be toxic if inhaled. These are rated on a scale from A+ (very low) to C (high).



Registration, Evaluation,  
Authorisation of Chemicals



PANAGET - 3 rue d'Orgères - 35230 Bourgarré - FRANCE  
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // [www.panaget.com](http://www.panaget.com)

# DECLARATION OF PERFORMANCE

N° 1000028



**Unique identification code of the product-type:** Sonate 90 Tongue & Groove, 14 mm, French oak

**Intended use/es:** Solid single plank made under the patent EN 13226

Glue down installation under the patent DTU 51.2

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

## Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> )	650	
- Average thickness (mm)	14	
- Intended use, fitting mode	Glued to the subfloor	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1µg/m <sup>3</sup>	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.17	EN 14342 / Chapter 4.7
Thermal resistance (m <sup>2</sup> .K/W)	0.08	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	8.5 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	1.4 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023

**Carole FRANÇOIS**

